

Sample ID	Condition	Individual Slip Index Determinations				Average Slip Index
		N	E	S	W	
ecoDUSTRIAL™ aquaBRIGHT™ polyFIBRO®	Dry	0.62	0.62	0.61	0.61	0.62
	Wet	0.32	0.29	0.27	0.23	0.28
ecoDUSTRIAL™ aquaBRIGHT™ polyFIBRO® Slip Resistant Textured Coatings	Dry	0.56	0.61	0.60	0.61	0.60
	Wet	0.37	0.36	0.39	0.45	0.39
Beach Entry Coatings	Dry	0.76	0.74	0.80	0.80	0.78
	Wet	0.77	0.69	0.73	0.70	0.72
ecoDUSTRIAL™ Non-Skid Coatings	Dry	0.81	0.78	0.86	0.68	0.78
	Wet	0.72	0.79	0.85	0.82	0.80